

Physical Properties Of Nitrogen Doped Amorphous Carbon Films From Ethanol Precursor For Solar Cell Applications

A. Ishak, M. Rusop

Abstract—The nitrogen doped amorphous carbon (a-C:N) thin films were synthesized for the first time by mixing of nitrogen gas, argon and ethanol precursor via a bias assisted pyrolysis-CVD in the range of 250°C to 550°C with fixed negative bias of -50V in 1h deposition. The a-C:N thin films were characterized by current-voltage measurement, UV/VIS spectrophotometer, surface profiler, and atomic force microscopy. The resistivity of a-C:N thin films in the range 250°C-550°C was $4.97 \times 10^7 \Omega \cdot \text{cm}$, $2.66 \times 10^5 \Omega \cdot \text{cm}$, $1.974 \times 10^4 \Omega \cdot \text{cm}$, $3.63 \times 10^3 \Omega \cdot \text{cm}$, and $4.44 \times 10^3 \Omega \cdot \text{cm}$, and $1.73 \times 10^4 \Omega \cdot \text{cm}$, respectively. It was found that a-C:N thin films have responded with photon by created electron hole pair where the highest photo response of a-C:N film was found at 350°C. The deposition temperatures with the help of constant dc voltage influenced the physical properties of a-C thin films.

Index Terms— Amorphous carbon, Ethanol precursor, Negative bias, Nitrogen doping, Carbon film

1 INTRODUCTION

A possibility of any hydrocarbon sources deposited directly from liquid precursor a to a vapor-phase state, growth onto non-crystalline substrate has a big advantage in technological viewpoint instead of high excellent in photoconductivity and high optical absorption of visible light [1-5]. The as-deposited (undoped) of amorphous carbon (a-C) is as weakly p-type in nature irrespectively with deposition method, deposition condition and precursor use. The a-C is reported as a complex structure and existing a high density of intrinsic defect [1-5] which contributed to the non ohmic form of slope, low conductivity and low photo-response, and therefore barrier to the well formation of p-n junction device solar cell. Furthermore, the difficulty for doping dopants such as nitrogen, boron and phosphorous incorporated with amorphous thin films for increase the conductivity is another issue to be concerned in improvement the deposited carbon thin films [6-8]. Until now, various standard deposition techniques are practically used [1-6] which have difference advantages of parameters. In this study, the nitrogen doped a-C thin films is deposited by mixing nitrogen gas, argon, and ethanol in the chamber using bias assisted pyrolysis-CVD. Among deposition parameters, positive bias voltage applied to the substrates could significantly change film properties due to enhancement of adatom mobility and the effects of ion bombardment. The ion bombardment during coating deposition would play an important role in affecting the morphology, structure, composition and mechanical properties of coatings [1-4]. Many attempts were studied by others on the effect of DC bias for instant through the use of pure lubricant coatings (MoS_2) composite film which was able to provide good lubricious property due to the strong basal plane orientation and application of a bias voltage was found to reduce the coefficient of friction [8-11]. In this paper, we studied the effect of deposition substrate temperature on the physical properties of nitrogen doped of a-C thin films using ethanol precursor. To our knowledge, preparation and study on physical properties of nitrogen dope by using ethanol prepared by this technique has been rarely reported by other research groups.

2 Experimental Detail

The cleaning of glass substrates has been reported elsewhere [1,3,7]. A schematic diagram of bias assisted pyrolysis-CVD is shown in Fig. 1. The ethanol was directly heated at around 65°C by using the hot platter (Stuart CB162). The vaporized ethanol was then pressured into the chamber by using two air pumps with a medium pressure. The amount of vapor of ethanol, argon pressured into the chamber was set at 100 mL/min, 150 mL/min, respectively. The argon gas was used for carrier of deposition particle onto the substrate and also to dispose contaminated particles outside the chamber. The samples were finally characterized by I-V measurement (Bukuh Keiki EP-2000), surface profiler (Veeco Dektak 150), JASCO UV-VIS/NIR Spectrophotometer (V-670 EX) and Park system XE-100 atomic force microscope (AFM) for electrical, thickness, optical, atomic level properties, respectively.




Fig. 1 A schematic diagram of bias assisted-pyrolysis-CVD

The deposition substrate temperature was set at 350°C for 1h deposition with a constant of negative bias voltage -20V and without negative bias (0 V). A liquid palm oil precursor was heated outside the chamber at 180°C by using hot platter (Stuart CB162). A vaporized of palm oil was pressured into the chamber using aquarium air pumps (GA8000). The amount of the vaporized palm oil, carrier gas argon used into were set to be constant at 114 mL/min, 180 mL/min, respectively. For doping process, 150mg of boron was placed on an aluminium foil inside the furnace chamber.

3 Result and Discussions




Fig. 2 A Current-voltage measurement of C:N thin films on the glass substrate

$$\rho = RA/L \tag{1}$$

$$\sigma = 1/\rho \tag{2}$$

Fig. 2 shows the current-voltage measurement of a-C:N film. An Aurum with fixed square area of approximately 0.09 cm² is sputtered as a metal contact on a-C:N film. The resistivity and conductivity are calculated by using both equation (1) and (2) [8,9], respectively where R is the average of resistance; A is the area of metal contact and L is the length between metal two contacts. There were many forms of I-V relationships obtained in the literatures such as linear (ohmic), slightly linear, and nonlinear forms [10,11]. There is a need to form the linear behavior between current and applied voltage which is important for solar cell application. Besides the ohmic behavior, more importantly, the low resistivity and high conductivity a-C thin films as a semiconductor are required for solar cells application. Gold as a metal contact along with semiconductor thin films was studied by many researcher [10,12]. Metals contact such as titanium (Ti), chromium (Cr), aluminum (Al) and argentum (Ag) can reacted differently with thin film [10,12]. It was found all of the slopes are in linear region when the voltage is applied from -15V to +15V. The highest slope was found at 550°C while the smallest slope contact was at 250°C. Zeng et al [12] and Liu et al [13] reported the nonlinearity was attributed to the existence and magnitude of schottky depends on the Fermi levels of semiconductor and conducting metal. Other possibility factor caused the nonlinearity were contributed by a dielectric layer formed between gold and semiconductor thin films.




Fig. 3 Current voltage relationships of a-C:N films at various deposition temperatures

The smaller slope might be due to the additional of resistance come from high density of intrinsic defects. Zeng et al [12] discussed that increasing temperature can changed the structural to form more crystallite thereby decreased the resistivity. The decreasing of the resistivity due to increasing temperatures was discussed by others [13-17].




Fig. 4 Resistivity and conductivity of a-C:N films at various deposition temperatures

Fig. 4 shows the variation resistivity and conductivity of a-C:N thin films at different deposition temperature in the range of 250°C to 550°C. The resistivity of a-C:N thin films is calculated as 4.97x10⁷ Ω.cm, 2.66x10⁵ Ω.cm, 1.974x10⁴ Ω.cm, 3.63x10³ Ω.cm, 4.44x10³Ω.cm, 1.85x10⁴ Ω.cm, and 1.73x10⁴ Ω.cm, respectively. S.M. Sze [15] summarized the resistivity range of semiconductors was in between 1x10⁸ to 1x10⁻³ Ω.cm and by comparing with our result, we have seen that the resistivity of a-C:N thin films are semiconductor thin film We predict that, a-C:N thin films might deform structure with dopant of nitrogen to provide excess of electron thereby reduce the number of defect of thin films. Beside other factors [13,14], deposition temperature is the main role to deform the existing structure together with crystallite form. The conductivity of doped a-C:N thin films is calculated by the reciprocal of resistivity values. Fig. 4 shows the correlation of conductivity with changing deposition temperatures. The values of conductivity is 2.02x10⁻⁸ Scm⁻¹, 3.76x10⁻⁶ Scm⁻¹, 5.05x10⁻⁵ Scm⁻¹, 5.78x10⁻⁵ Scm⁻¹, 2.75x10⁻⁴ Scm⁻¹, and 2.25x10⁻⁴ Scm⁻¹, respectively. The conductivity of a-C:N thin films is gradually increased by the decreasing of substrate deposition temperature 250°C to 550°C. The effect of increasing deposition temperature and doping on the increment of conductivity of thin films were also agreed and discuss by others [18-22]. A photo response is defined as the ratio of conductivity under illumination to the conductivity under dark. Table 1 shows the effect of the temperature parameters on the photo response. The values of photo response from 250°C to 550°C are 1.3722, 1.1331, 4.3779, 1.4807, 1.0271, and 1.0314, respectively. The results showed the photo response is slightly decreased from 250°C to 300°C and showed dramatically increased from 300oC to 350°C. However, at 400°C to 500°C, it was strongly decreased. We found, the highest value of photo response is at 350°C while the lowest value is at 450°C. By comparing with sloped metal contact, resistivity, conductivity, and photo response results, at 350°C is the optimum deposition temperature. Table 1 shows the influenced of temperature toward the thickness of a-C thin films. The average of thickness in the range of 250°C to 550°C is 250 nm, 230 nm, 420 nm, 103.2 nm, 383.2 nm, and 680 nm respectively. From Table 2, the highest thickness is found at

550°C while the lowest average thickness is 230nm at 300°C. We found, the average thickness is strongly dependence with deposition temperature. However, the increasing of average thicknesses was not influenced resistivity as well as conductivity.




Fig.5. The AFM images of a-C thin films by in-situ doped at various temperatures

AFM images of a-C:N thin films were characterized by atomic force microscopy (AFM, XE-100 Park Systems), as shown in Fig. 5 with a scan rate 1Hz and scan size of 10 μ m. The images show different forms of particles on the surface for all a-C:N thin films. The surface roughness from 250°C to 550°C are 1.842, 0.828, 0.053, 0.244, 0.828, and 1.448 nm while the average grain sizes are 0.802, 0.935, 0.124, 0.661, 0.526, and 0.326, respectively.

Table 2 The surface roughness and average grain size of a-C:N thin films in the range of 250°C-550°C

Temperature (°C)	Surface Roughness (nm)	Average Grain Size (μ m ²)
250°C	1.842	0.802
300°C	0.82	0.935
350°C	0.053	0.124
400°C	0.244	0.661
450°C	0.828	0.526
550°C	1.148	0.326

The highest surface roughness is 1.842 at 250°C while the lowest surface roughness is 0.053 at 350°C. For the average grain size, 0.935 is the highest average grain size at 300°C while 0.526 is the lowest average grain size at 450°C. It is believed that grain boundary and surface roughness are

directly related with the electrical properties especially carrier concentration and mobility of the electron. It was observed that both surface roughness and conductivity were decreased as the temperature was increased from 250°C to 300°C. Furthermore, the conductivity is strongly increased when the surface roughness was decreased. Similarly, the conductivity was increased as the average grain size was decreased. The effects of grain boundary and surface roughness on electrical properties were also reported by other [20-23]. AFM measurement reveals the average grain sizes for the sample at 250°C is the highest as compared with others temperatures and therefore restricts the ability for electron movement. Huang et al [23] reported thickness could also affect the conductivity. In our experiment, we found as the thickness increased, the average grain size is increased causing to decreasing the conductivity. This difference in the size of the surface film can be attributed to the ion bombardment during the growth of the films which is controlled by the applied of negative bias onto the substrate.

CONCLUSION

The semiconducting a-C:N thin films was successfully deposited by bias assisted pyrolysis-CVD from ethanol precursor. The resistivity of a-C:N thin films deposited at 250°C to 550°C were $4.97 \times 10^7 \Omega \cdot \text{cm}$, $2.66 \times 10^5 \Omega \cdot \text{cm}$, $1.974 \times 10^4 \Omega \cdot \text{cm}$, $4.44 \times 10^3 \Omega \cdot \text{cm}$, $1.85 \times 10^4 \Omega \cdot \text{cm}$, and $3.63 \times 10^3 \Omega \cdot \text{cm}$, respectively. Meanwhile, the conductivity of a-C:N thin films were $2.012 \times 10^{-8} \text{ Scm}^{-1}$, $3.76 \times 10^{-6} \text{ Scm}^{-1}$, $5.05 \times 10^{-5} \text{ Scm}^{-1}$, $5.78 \times 10^{-5} \text{ Scm}^{-1}$, $2.75 \times 10^{-4} \text{ Scm}^{-1}$, and $2.25 \times 10^{-4} \text{ Scm}^{-1}$, respectively. The resistivity was decreased as the temperature increased. The highest and the lowest photo response of a-C:N film were found at deposition temperature of 350°C, and 250°C, respectively.

ACKNOWLEDGMENT

The authors thank to Ministry of Higher Education (MOHE) Malaysia, Universiti Teknologi MARA, Kota Samarahan Sarawak for the scholarship and Research Management Institute (RMI) Universiti Teknologi MARA (UiTM) for the facilities.

REFERENCES

- [1] A. Ishak, K. Dayana, M. H. Mamat, M. F. Malek, and M. Rusop, Deposition of Amorphous Carbon Film Using Natural Palm Oil by Bias Assisted Pyrolysis-CVD For Solar Cell Applications, Inter. J. Power and Renew. Energy Sys. 1 (2014) 12-23.
- [2] S. M. Mominuzzaman, M. Rusop, T. Soga, T. Jimbo, and M. Umeno, "Photoresponse characteristics of nitrogen doped carbon/P-silicon photovoltaic cell," IEEE 4th World on Conference on Photovoltaic Energy Conversion, vol. 1, pp. 302-305, 2006.
- [3] A. Ishak, M. Rusop, "Structural Properties of Micro and Nanostructured Amorphous Carbon Films from Liquid Hydrocarbon Precursor in Photovoltaic Heterojunction Solar Cell Applications", published in International Journal of Latest Research in Science and Technology vol. 3 (2014) pp. 90-94.
- [4] O. Cubero, F. j. Haug, D. Fisher, and C. Ballif, "Reduction of the phosphorus cross-contamination in n-i-p solar cells

- prepared in a single-chamber PECVD reactor," *J. Solar Energy Materials & Solar Cells*, vol. 95, pp. 606-610 2011.
- [5] C. Corbell, M. Rubio-Roy, E. Bertran, and J. L. Andujar, "Plasma parameters of pulsed-dc discharge in methane used to deposit diamondlike carbon films," *J. Applied Physics*, vol. 106, pp. 103302-10302-11, 2009.
- [6] A. Mallikarjuna Reddy, A. Sivasangkar Reddy, and P. Sreedhara Reddy, "Effect of substrate bias voltage on the physical properties of dc reactive magnetron sputtered NiO thin films," *J. Material Chemistry and Physics* vol. 125, pp. 434-439, 2011. J. Podder, M. Rusop, T. Soga, T. Jimbo, Boron doped amorphous carbon films grown by r.f. PECVD under different partial pressure, *Diamond and Related Materials* 14 (2005) 1799-1804.
- [7] A. Ishak, M. Rusop, "Structural Properties of P-Type Boron Doped Carbon Film from Hydrocarbon Palm Oil for Photovoltaic Heterojunction Solar Cell Device", published in *International Journal of Engineering Invention* vol. 3 (2014) pp. 35-41.
- [8] A. Ishak M. Amirul, and M. Rusop, "AFM images of undoped amorphous carbon thin films deposited by bias-assisted thermal-CVD," 10th International Conference on Semiconductor Electronics (ICSE2012), 2012.
- [9] H. Hussin, F. Mohamad, S. M. A. Hanapiah, M. Muhammad, and M. Rusop, "Electrical properties of a-C thin film deposited using methane gas as precursor," International Conference on Electronic Devices, System and Application (ICEDSA2010), 2010.S.
- [10] J. Krauser, A. K. Nix, H. G. Gehrke, H. Hofsaess, C. Trautmann, and A. Weidinger, "Conductivity enhancement of ion tracks tetrahedral amorphous carbon by doping with N, B, Cu and Fe," *Nuclear Instruments and Methods in Physics Research B*, vol.272, pp. 280-283, 2012.
- [11] F.M. Wang, M.W. Chen, and Q.B. Lai, "Metallic contacts to nitrogen and boron doped diamond-like carbon films," *Thin Solid Films*, vol. 518, pp. 3332-3336, 2010.
- [12] A.P. Zeng, Y.B. Yin, M. Bilek, and D. McKenzie, "Ohmic contact to nitrogen doped amorphous carbons films," *Surface Coating Technology* 198 (2005) 202.
- [13] A. Bubenzer, B. Dischler, G. Brandt, P. Koids, rf-plasma deposited amorphous hydrogenated hard carbon thin films: preparation, properties, and applications, *Journal of applied Physics* 54 (1983) 4590.
- [14] Peng Wang, Xia Wang, Youming Chen, Guangan Zhang, Weimin Liu, Junyan Zhang, The effect of applied negative bias voltage on the structure of Ti-doped a-C:h films deposited by FCVA, *Applied Surface Science* 253 (2007) 3722-3726.
- [15] S.M. Sze, *Semiconductor devices physics and technology*, Wiley 1985.
- [16] F. Buebuel, I. Efeoglu, E. Arslan, The effect of bias voltage and working pressure on S/Mo ratios at MoS₂-Ti composite films, *Applied Surface Science* (2007), 253-44515-9.
- [17] M. Sakaki, T. Sakakibara, Ionization and reaction mechanism of a reactive cathodic arc deposition of TiN. *IEEE Trans Plasma Science* (1994) 22.
- [18] M. S. Leu, S. Y. Chen, J. J. Chang,, et al. Diamond-like coatings prepared by the filtered cathodic arc technique for minting application, *Surface Coating Technology* 177-178 (2004) 566.
- [19] Dwivedi, Neeraj Kumar, Sushil Malik, and K. Hitendra, "Studied on pure and nitrogen-incorporated hydrogenated amorphous carbon thin films and their possible application for amorphous silicon solar cells," *Journal of Applied Physics*, vol. 111, pp. 14908-14916, Jan. 2012.
- [20] R. Gharbi, M. Fathallah, N. Alzaied, E. Tresso, and A. Tagliaferro, "Hydrogen and nitrogen effects on optical and structural properties of amorphous carbon," *Mater. Sci. Eng. C*, vol. 28, pp. 795, 2008 .
- [21] L. Y. Huang, L. Meng, "Effects of films thickness on microstructure and electrical properties of the pyrite films," *Mater. Sci. Eng. B*, vol. 137, pp. 310, 2007.
- [22] E. Liu, L. Li, B. Blainpain, Residual stresses of diamond and diamondlike carbon films, *Journal of Applied Physics*, 98 (2005) 073515.
- [23] Hiroki Akasaka, Takatoshi Yamada, and Naoto Ohtake, "Effect of film structure on field emission properties of nitrogen doped hydrogenated amorphous carbon films," *Journal In Diamond & Related Materials*, vol. 18, pp. 423-425, 2009. B. Suriani, A.A. Azira, S.F. Nik, Roslan Md Nor, and M. Rusop, Synthesis of vertically aligned carbon nanotubes using natural palm oil as carbon precursor, *Material Letters* 63 (2009) 2704-2706.